

Synthesis of nanocrystalline ZnCeO₂ by sol- Gel method

N.K.JAVIR¹,S.R.BAMANE²

¹ Department of Chemistry J. J.T .University Rajasthan, India

² Raja shripatrao Bhagawantrao Mahavidyalay Aundh (Satara),Maharashtra state Pin - 415510

ABSTRACT: ZnCeO₂ nanoparticles were successfully synthesized by Sol-gel technique. It is simple , rapid and more effective technique for synthesis metal oxide and mixed oxide ZnCeO₂ .Two type of sample synthesized at different temperature 200^o C and 400^o C of different thermal annealing sources .The synthesized ZnCeO₂ nanoparticles characterized by scanning electronic microscopy (SEM) and X-ray diffraction method SEM image reveal that spherically shape The of synthesized sample is highly crystalline and size of particles of ZnCeO₂ found to be 14 nm.by XRD analysis

Keywords :-Sol –gel process , ZnCeO₂ Nanoparticals ,XRD, SEM.

1.Introduction

ZnCeO₂Mixed oxide is photocatalyst , due to its photocatalytic activity it has wide application.The different chemical methods employed to synthesis of nanocrystalline like sol- gel method[1],[2] ,[3] sonochemically [4]], [5],co-precipitation[6],solvothral technique [7],,microwave synthesis [8],[9] etc. Out of these sol- gel process has many advantages and it is the most practical process in preparation of porous ceramic membrane. By this method synthesis of metal oxide and mixed metal oxide have superior homogeneity and well defined pore size distribution and a better control over the micro structural properties of the nanocrystal [10] .mostly the nanoparticles synthesized by sol gel- process and amorphous in nature and it require further heat treatment process for the production of crystalline particles[11] .The sol-gel process is wet chemical technique .Recently the sol-gel technology is widely used in the fields of material science and ceramic engineering .It is an effective technique to synthesis nanoparticles due to its high production rate and rapid productivity of fine homogeneous powder. It has low processing cost high activity,good atomic efficiency and rapid response to changing condition in catalyst system.

The present work focus on the synthesis nanocrystals of ZnCeO₂ by sol-gel process .These nanoparticles are characterized by XRD diffraction and morphology of nanocrystalline were investigated by scanning electron microscopy(SEM)

2. EXPERIMENTAL

ZnCeO₂nanoparticales were synthesised by sol-gel method .All the chemical used in the experiment were analytically grade and were used without further purification. Nanoparticles were synthesised by mixing 100 ml(0.1M) zinc nitrate Zn(NO₃)₂. 6H₂O 100ml (0.1M)Ammonium ceric nitrate (NH₄)₂Ce(NO)₂ by stirring 45 min. followed by added 50 ml(0.1M) citric acid solution dropwise with vigorous stirring .The resulting solution turned to yellowish .The reaction mixture was then heated at about 80^o C for 2 Hours with continuously magnetic stirring until the gel was formed. The gel was dried in oven at 100^o C for 2 Hrs. which leads the formation of light weight porous materials due to the evolution of gas. It was sintered at 200^oC for 3 hrs in oven and another sample annealed at about 400^oC fo 2 hrs in mufale furnace to get fine homogeneous dense powder.Crystals of ZnCeO₂ .Powderwas washed with de-ionised water for several times to remove unreacted impurities. Synthesised powder characterized by SEM and XRD.

3.RESULT AND DICUSSION

3.1 XRD Patterns of the SamplesThe x-ray diffraction of synthesized ZnCeO₂ oxide studied using cu radiation(1.5406A0).The synthesized nanoparticles were pure .All the diffraction peak are rather sharpe which indicate the ZnCeO₂ sample has high degree of crystallinity.The characteristic peak are observed at 2 θ values at 28.2. From XRD data crystalline size synthesized ZnCeO₂ particles was estimated by De-bye scherrers equation $D_p=0.9\lambda/\beta\cos\theta$ where D_p is the size of particle in nm , λ is wavelength of x-ray (1.5406) and β is the full width at half maximum (FWHM) and θ is the diffraction peak angle.XRD pattern of synthesied ZnCeO₂is structural properties.The average partical size of nanocrystals calculated with XRD and it is found 14 nm.




Figure (a) XRD of nanocrystalline ZnCeO₂

3.2 SEM image of ZnCeO₂

SEM analysis of Synthesized ZnCeO₂ shown that completely different surface morphology behavior due to effect of different heat treatment. SEM image reveals **nanoparticles is spherical shaped**.




Fig. (b)






Fig.(c)

Fig. (b) and (c) SEM image of ZnCeO₂ sample annealed at 200°C.



(e)
(d)

Fig. (d) and (e) SEM image of ZnCeO_2 sample annealed at 400°C

5. CONCLUSION

Sol-gel method to synthesis ZnCeO_2 has been successfully established. This method is effective to control morphological and structural properties. The average partical size of nanocrystals calculated with XRD and it is found 14 nm. The SEM image of synthesized mixed oxide ZnCeO_2 shows different morphological behaviour at different annealing temperature 200°C

REFERENCES

- [1] S Ramesh Sol-gel synthesis and characterization of $\text{Ag}_{3(2+x)}\text{AlxTi}_4\text{O}_{(11+s)}$ nanoparticles Journal of nanoscience pp 1-9, 2013
- [2] Davood Raoufi, Taha Raoufi The effect of heat treatment on the physical properties of sol-gel derived ZnO thin films Applied Surface Science pp1-6, 2009
- [3] Mauro, Epifan, Cinzia Giannini Leander Tapfer and Lorenzo Vasaoelli [2000] Sol-Gel Synthesis and characterization of Ag and Au nanoparticles in SiO_2 , TiO_2 and ZrO_2 Thin films Journal of American Ceramic Society, 83(10), pp 2385-93.
- [4] Askarinjad, Azadeh, Alavi, Mohammad Arvin, Morsaliali. Sonochemically Synthesis of ZnO nano Particles A Novel Direct method. Iran J. Chem Eng. vol.30, no. 3, pp 75-81, 2011
- [5] Masoun Salavati-Niasari, Chader-Hosseinzadeh, Fatemeh Davar Synthesis of Lanthanum Hydroxide And Lanthanum Oxide Nanoparticles by Sonochemical Method. journal of alloys and compounds .vol. 509, pp. 4098-4103, 2011
- [6] Harish kumar Manisha and poonamsangwan synthesis and characterization of MnO_2 Nanoparticals using Coprecipitation Technique. International journal of chemistry and chemical engineering vol. 3, no.3, pp. 155-160., 2013
- [7] E. Kumar, P. Selvarajan, D. Muthuraj. Synthesis and characterization of CeO_2 nanocrystals by Solvothermal route. Material Research vol.16 no.2, pp1-6, 2013.
No.3 PP.71-77,
- [8] A. Gleyva, P. Stoliar, M. Rosenbusch, V. Lorenzo, P. Levy, Albonetti, M. Cavallini, F. Biscarini, H. E. Troiani, J. Curiale, R. D. Sanchez. Microwave assisted synthesis of manganese mixed oxide nano structures using plastic templates. Journal of solid state chemistry vol.117, pp. 3949-3953, 2004
- [9] Fipires, E. Joanni, R. Savu, M. A. Zaghete, E. Longo, J. A. Vrala Microwave-Assisted Hydrothermal Synthesis of Nanocrystalline SnO Powders. Material Science vol. 62, pp.239-242, 2008.
- [10] Sh. Akbarnezhad, S. M. Mousavi and R. Sarhaddi Sol-gel Synthesis of alumina-titania ceramic membrane: Preparation and characterization. Indian Journal of Science and Technology. Vol.3 no.10, pp 1048-1051, 2010
- [11] T. Suresh and Annadurai [2013] synthesis, characterization and photocatalytic degradation of malachite green dye using titanium dioxide Nanoparticles. International journal of research in Environmental science and Technology. Vol.3, no.3, pp.71-77, 2013